

DTIC FILE

4

AD-A208 727

OFFICE OF NAVAL RESEARCH

CONTRACT NOOO 14-85-0177

R & T Code 431a003-4

Technical Report No. 11

GROWTH AND CHARACTERIZATION OF ZINC SULFIDE FILMS BY
CONVERSION OF ZINC OXIDE FILMS WITH H_2S

by

Y-M. Gao, P. Wu, J. Baglio*, K. Dwight and A. Wold

Prepared for Publication in
Materials Research Bulletin

May 30, 1989

Brown University
Department of Chemistry
Providence, RI 02912

*GTE Labs, Inc., Waltham, MA 02254

Reproduction in whole or in part is permitted for any
purpose of the United States Government

This document has been approved for public release and sale;
its distribution is unlimited

DTIC
ELECTE
JUN 06 1989
S H D

89

6

05

182

REPORT DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION UNCLASSIFIED			1b. RESTRICTIVE MARKINGS	
2a. SECURITY CLASSIFICATION AUTHORITY			3. DISTRIBUTION / AVAILABILITY OF REPORT APPROVED FOR PUBLIC RELEASE DISTRIBUTION UNLIMITED	
2b. DECLASSIFICATION / DOWNGRADING SCHEDULE				
4. PERFORMING ORGANIZATION REPORT NUMBER(S) # 11			5. MONITORING ORGANIZATION REPORT NUMBER(S) N00014-85-0177	
6a. NAME OF PERFORMING ORGANIZATION BROWN UNIVERSITY AARON WOLD		6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION OFFICE OF NAVAL RESEARCH DR. R. SCHWARTZ	
6c. ADDRESS (City, State, and ZIP Code) DEPARTMENT OF CHEMISTRY PROVIDENCE, RI 02912			7b. ADDRESS (City, State, and ZIP Code) CODE 3854 NAVAL WEAPONS CENTER CHINA LAKE, CA 93555	
8a. NAME OF FUNDING / SPONSORING ORGANIZATION		8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER	
8c. ADDRESS (City, State, and ZIP Code)			10. SOURCE OF FUNDING NUMBERS	
			PROGRAM ELEMENT NO.	PROJECT NO.
			TASK NO.	WORK UNIT NO.
11. TITLE (Include Security Classification) GROWTH AND CHARACTERIZATION OF ZINC SULFIDE FILMS BY CONVERSION OF ZINC OXIDE FILMS WITH H ₂ S.				
12. PERSONAL AUTHOR(S) N-M. Gao, P. Wu, J. Baglio, K. Dwight and A. Wold				
13a. TYPE OF REPORT Technical		13b. TIME COVERED FROM _____ TO _____	14. DATE OF REPORT (Year, Month, Day) May 30, 1989	15. PAGE COUNT 7
16. SUPPLEMENTARY NOTATION PREPARED FOR PUBLICATION IN MATERIALS RESEARCH BULLETIN				
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB-GROUP		
19. ABSTRACT (Continue on reverse if necessary and identify by block number) Zinc sulfide films were prepared by conversion of zinc oxide films in the presence of hydrogen sulfide. The films which contained both the hexagonal and cubic forms of zinc sulfide were shown to be uniform and gave a measured band gap of 3.65 eV. The electrical resistances of the films prepared were greater than 10 ⁷ Ω.				
20. DISTRIBUTION / AVAILABILITY OF ABSTRACT <input type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION	
22a. NAME OF RESPONSIBLE INDIVIDUAL			22b. TELEPHONE (Include Area Code)	22c. OFFICE SYMBOL

GROWTH AND CHARACTERIZATION OF ZINC SULFIDE FILMS
BY CONVERSION OF ZINC OXIDE FILMS WITH H_2S

Y-M. Gao, P. Wu, J. Baglio+, K. Dwight and A. Wold
Department of Chemistry, Brown University
Providence, RI 02912

+GTE Labs, Inc., Waltham, MA 02254

ABSTRACT

(10 to the 7th of 11)
Zinc sulfide films were prepared by conversion of zinc oxide films in the presence of hydrogen sulfide. The films which contained both the hexagonal and cubic forms of zinc sulfide were shown to be uniform and gave a measured band gap of 3.65 eV. The electrical resistances of the films prepared were greater than $10^7 \Omega$.

MATERIALS INDEX: Zinc oxide, Zinc sulfide

Introduction

2.
Zinc sulfide is an IR window material and a transparent semiconductor with a large direct band gap. It also possesses piezoelectric, photoconductive and electroluminescent properties. Thin films of zinc sulfide can be utilized for infrared antireflection coatings, light-emitting diodes (LEDs), electroluminescent (EL) displays, multilayer dielectric filters, optical phase modulation and light guiding in integrated optics. In recent years, there has been a large amount of effort directed at the growth of high quality films of ZnS. Various fabrication techniques have been employed, such as ion beam sputtering (1), atomic layer epitaxy (ALE) (2), molecular beam epitaxy (MBE) (3), metal-organic chemical vapor deposition (MOCVD) and spray pyrolysis (4).

Recently, a novel ultrasonic nebulization and pyrolysis method has been developed in this laboratory (5). High quality films of zinc oxide can be grown using this simple technique. Previously, Maruska (7) reported the conversion of CdO films to CdS films by an ion exchange process. It therefore appeared feasible to convert ZnO films with H_2S into ZnS films.

Experimental

Preparation of zinc sulfide films

Zinc sulfide films were prepared by sulfurization of zinc oxide films with hydrogen sulfide. Zinc oxide films on silicon and silica substrates were prepared by ultrasonic nebulization of zinc acetate solutions and thermal

Characterization

Optical measurements of the films on silica substrates were performed using a Cary Model 17 dual beam ratio recording spectrophotometer in the range of 300 nm to 1500 nm. The optical band gap was determined from the transmittance near the absorption edge. Infrared spectra at room temperature were obtained on a Perkin-Elmer 580 single-beam scanning infrared spectrophotometer at an instrumental resolution of 2.8 cm^{-1} . The measurements were performed in the transmission mode over the range $2.5\text{ }\mu\text{m} - 25\text{ }\mu\text{m}$. Transmission through the sample was normalized to the signal obtained in the absence of sample.

Results and Discussion

X-ray diffraction analysis was used to determine the appropriate conditions for the conversion. It was desired that the conversion should be carried out at the lowest possible temperature, provided the reaction can be completed. It was found that after annealing in H_2S at $430^\circ C$ for 1 1/2 hrs, a film of $1\mu m$ thickness still contained a large amount of zinc oxide. The peaks



Codes
/or

A-1

of ZnO disappeared in patterns of such films after an anneal was performed at 500°C for 3 hrs in H₂S. No impurity phase could be detected.

X-ray diffraction analysis was performed on the zinc sulfide films as deposited on the substrates. The diffraction patterns showed that the films consisted of ZnS crystallized as a mixture of cubic and hexagonal phases. Both structures consist of close-packed sulfur planes with zinc atoms occupying half of the tetrahedral sites. The only difference between them is in the stacking sequence of the anion planes. Hexagonal zinc sulfide films can therefore partially convert to the more stable cubic zinc sulfide form under the conditions of film preparation. This apparently occurs without any appreciable reduction in the quality of the final film which is formed. Two phase zinc sulfide films have also been reported by previous investigators (9).

The prepared zinc sulfide films were examined with scanning electron microscopy. They showed a uniform grain texture and the particle size grew larger with thicker films. This is similar to the properties of the precursor zinc oxide films (8). Fig. 1 shows a picture of a film with a thickness of 1 μ m. The surface of the film showed a submicron grain texture with the size of most particles being about 0.3 μ m. Some films were analyzed with EDS. The results confirm the presence of ZnS with 50.2 atomic percent zinc and 49.8 atomic percent sulfur.

ZnS films have been found suitable as single-layer antireflection coatings in the region from 8 to 15 μ m (10). For the ZnS films deposited in this study onto silicon, infrared spectroscopic measurements were performed. Fig. 2 shows the measured transmittance of a 0.5 mm thick silicon wafer uncoated and coated with a single layer of ZnS of 1.15 μ m on each side. The transmittance at 10 μ m ($n_1 d_1 = \lambda/4$) is increased from 50 to 86% and remains above 70% from 7.3 μ m to 15 μ m. The maximum transmittance for such a sample can be calculated to be 93% at $\lambda = 10 \mu$ m (11). Thus the antireflection performance of our ZnS films was close to the theoretical value.

Fig. 3 shows the infrared spectra of zinc oxide and zinc sulfide films on silicon substrates in the range from 200 cm⁻¹ to 600 cm⁻¹. The strong band of the principal lattice absorption can be clearly seen at 280 cm⁻¹. Zinc oxide films have a broad absorption band with the peak at 410 cm⁻¹, which is consistent with Collins' results obtained from the reflectivity of a zinc oxide single crystal (12). The peak position of the absorption band of the zinc sulfide films was at 278 cm⁻¹. Kwasniewski (13) reported a broad absorption band covering 250 - 355 cm⁻¹ in the infrared transmission spectrum of cubic ZnS. Detailed information near the peak was not given because single crystals were used that were much thicker than thin films. Brafman (14) reported that the fundamental resonance frequencies of zinc sulfide with the hexagonal and cubic structures were 273 and 276 cm⁻¹, respectively, which is verified by the recent work of Memon (15). These results are all consistent with the results obtained in this investigation. Infrared spectra of zinc sulfide films was used as a means of verifying the completion of conversion of ZnO to ZnS. It is shown in Fig. 3 that a film partially converted to sulfide has both absorption band characteristics of zinc sulfide and zinc oxide.

The optical transmission of zinc sulfide films on silica substrates was measured and the transmission near the absorption edge was used to generate the plot of $(ah\nu)^2$ versus $h\nu$ as shown in Fig. 4. The intercept of the plot gave the energy of the direct band gap. It was found that the direct band gap of the prepared zinc sulfide films was 3.65 eV, which is consistent with the value given in the literature (4).




Fig. 1. Photomicrograph of a zinc sulfide film with a measured thickness of 1 μm . The grains average 0.3 μm in diameter.




Fig. 2. Transmission spectrum of a silicon wafer 0.5 mm thick coated with a 1.15 μm layer of ZnS on each side.




Fig. 3. Comparative infrared spectra of films of untreated zinc oxide, zinc oxide partially converted to the sulfide, and of fully converted zinc sulfide.




Fig. 4. Determination of the direct optical band gap of zinc sulfide.

When attempts were made to measure the electrical resistance of zinc sulfide films of about 0.4 μm thickness, it was found that the resistance was always greater than the limit of the instrument used, namely $10^7 \Omega$.

Conclusions

This study has demonstrated the preparation of zinc sulfide films by the conversion of zinc oxide films to zinc sulfide in the presence of H_2S . Zinc oxide films were prepared as a precursor by ultrasonic nebulization of zinc acetate solution followed by decomposition of the zinc acetate to zinc oxide. Uniform films of ZnS with good adherence have been obtained using this technique. The transparent polycrystalline films have submicron grain texture with a bandgap of 3.65 eV. They showed potential as an IR antireflection coating material.

Acknowledgements

This research was partially supported by the Office of Naval Research, by the National Science Foundation Contract No. DMR 8803184, by GTE Labs, Inc. Waltham, MA, and by Eastman Kodak Company, Rochester, NY. The infrared spectra were obtained with the assistance of Ted Kirst.

References

1. T. E. Varitimos and R. W. Tustison, Thin Solid Films, 151, 27 (1987).
2. A. Hunter and A. H. Kitai, J. Cryst. Growth, 91, 111 (1978).
3. M. Kitagawa, Y. Tomomura, A. Suzuki and S. Nakajima, J. Cryst. Growth, 95, 509 (1989).
4. S. Yamaga, A. Yoshikawa and H. Kasai, J. Cryst. Growth, 86, 252 (1988).
5. H. L. Kwok and Y. C. Chau, Thin Solid Films, 66, 303 (1980).
6. W. DeSisto, M. Sosnowski, F. Smith, J. DeLuca, R. Kershaw, K. Dwight and A. Wold. Submitted to Materials Research Bulletin.
7. H. P. Maruska, A. R. Young, II, and C. R. Wronski, 15th IEEE Photovoltaics Specialists Conference, p. 1030 (1981).
8. P. Wu, Y-M. Gao, J. Baglio, R. Kershaw, K. Dwight and A. Wold, Submitted to Chemistry of Materials.
9. B. Greenberg, W. K. Zwickler and I. Cadoff, Thin Solid Films, 141, 89 (1986).
10. J. T. Cox and G. Hass, Physics of Thin Films, 2, 239 (1964).
11. O. S. Heavens, Physics of Thin Films, 2, 193 (1964).
12. R. J. Collins and D. A. Kleinman, J. Phys. Chem. Solids, 11, 190 (1959).

13. E. A. Kwasniewski, E. S. Koteles and W. R. Datars, Can. J. Phys., 54, 1053 (1976).
14. O. Brafman and S. S. Mitra, Phys. Rev., 171, 931 (1968).
15. A. Memon and S. B. Tanner, Phys. Stat. Sol. B, 128, 49 (1985).